NBS TECHNICAL NOTE **1149**

Short-Term Evaluation Procedures for Coatings on Structural Steel

NATIONAL BUREAU OF STANDARDS

The National Bureau of Standards[1] was established by an act of Congress on March 3, 1901. The Bureau's overall goal is to strengthen and advance the Nation's science and technology and facilitate their effective application for public benefit. To this end, the Bureau conducts research and provides: (1) a basis for the Nation's physical measurement system, (2) scientific and technological services for industry and government, (3) a technical basis for equity in trade, and (4) technical services to promote public safety. The Bureau's technical work is performed by the National Measurement Laboratory, the National Engineering Laboratory, and the Institute for Computer Sciences and Technology.

THE NATIONAL MEASUREMENT LABORATORY provides the national system of physical and chemical and materials measurement; coordinates the system with measurement systems of other nations and furnishes essential services leading to accurate and uniform physical and chemical measurement throughout the Nation's scientific community, industry, and commerce; conducts materials research leading to improved methods of measurement, standards, and data on the properties of materials needed by industry, commerce, educational institutions, and Government; provides advisory and research services to other Government agencies; develops, produces, and distributes Standard Reference Materials; and provides calibration services. The Laboratory consists of the following centers:

Absolute Physical Quantities[2] — Radiation Research — Thermodynamics and Molecular Science — Analytical Chemistry — Materials Science.

THE NATIONAL ENGINEERING LABORATORY provides technology and technical services to the public and private sectors to address national needs and to solve national problems; conducts research in engineering and applied science in support of these efforts; builds and maintains competence in the necessary disciplines required to carry out this research and technical service; develops engineering data and measurement capabilities; provides engineering measurement traceability services; develops test methods and proposes engineering standards and code changes; develops and proposes new engineering practices; and develops and improves mechanisms to transfer results of its research to the ultimate user. The Laboratory consists of the following centers:

Applied Mathematics — Electronics and Electrical Engineering[2] — Mechanical Engineering and Process Technology[2] — Building Technology — Fire Research — Consumer Product Technology — Field Methods.

THE INSTITUTE FOR COMPUTER SCIENCES AND TECHNOLOGY conducts research and provides scientific and technical services to aid Federal agencies in the selection, acquisition, application, and use of computer technology to improve effectiveness and economy in Government operations in accordance with Public Law 89-306 (40 U.S.C. 759), relevant Executive Orders, and other directives; carries out this mission by managing the Federal Information Processing Standards Program, developing Federal ADP standards guidelines, and managing Federal participation in ADP voluntary standardization activities; provides scientific and technological advisory services and assistance to Federal agencies; and provides the technical foundation for computer-related policies of the Federal Government. The Institute consists of the following centers:

Programming Science and Technology — Computer Systems Engineering.

[1]Headquarters and Laboratories at Gaithersburg, MD, unless otherwise noted; mailing address Washington, DC 20234.
[2]Some divisions within the center are located at Boulder, CO 80303.

Short-Term Evaluation Procedures for Coatings on Structural Steel

NBS technical note

Paul G. Campbell
Jonathan W. Martin
Mary E. McKnight

Center for Building Technology
National Engineering Laboratory
National Bureau of Standards
Washington, DC 20234

U.S. DEPARTMENT OF COMMERCE, Malcolm Baldrige, Secretary

NATIONAL BUREAU OF STANDARDS, Ernest Ambler, Director

Issued September 1981

National Bureau of Standards Technical Note 1149
Nat. Bur. Stand. (U.S.), Tech. Note 1149, 43 pages (Sept. 1981)
CODEN: NBTNAE •

ABSTRACT

This report presents the findings of the first of a two-phased study to aid the Federal Highway Administration in evaluating and selecting protective coatings for steel. The objectives of the study are to review existing short-term test procedures for selecting coatings, and to discuss analytical measurement techniques for characterizing coating systems and for monitoring coating degradation.

In assessing current accelerated aging testing procedures, several deficiencies became apparent. These included the reported lack of reproducibility in the rankings for different iterations of the same short-term test and the lack of correlatability between the rankings of short-term laboratory and long-term outdoor exposure tests.

It was concluded that, at the present time, coating manufacturers and users do not depend heavily on accelerated test results for making durability assessments. Instead, durability assessments are based on outdoor exposure performance. Recommendations are made to design future short-term test procedures using reliability theory.

Key words: accelerated aging tests; coatings; corrosion; time to failure; predictability; reproducibility.

TABLE OF CONTENTS

TABLE OF CONTENTS (cont.)

ACKNOWLEDGMENT

1. INTRODUCTION

1.1 BACKGROUND

The high frequency of failures of protective coatings on State and local highway bridges, signs, barriers, etc., contributes to the large economic losses from corrosion experienced in the United States. A recent report, proposing a model for predicting corrosion costs on highway structural steel [1], estimated that the total expenditure for corrosion protection of steel bridges amounts to $130 - 160 million per year; and according to the author's model, this expenditure should be doubled to obtain maximum bridge service life.

An essential first step in maximizing service life is selecting the best available coating for the expected environmental and operating conditions. In making this selection, quantitative estimates of the service lives of candidate systems should be available for the wide range of environmental conditions experienced in the United States. Traditional sources for obtaining estimates are short-term laboratory tests and outdoor exposure tests. Currently, outdoor exposure results are heavily relied upon for service life predictions.

Over the last few years, however, changes have occurred jeopardizing the reliance on outdoor exposure tests for durability assessments. These changes have resulted from legislation aimed at 1) reducing solvent emissions (Federal Clean Air Acts of 1970 and 1977) and 2) lessening worker exposure to hazardous materials (Occupational Safety and Health Act, and Hazardous Material Acts). The effect of this legislation, along with oil import restrictions, has been to supplant many traditional coating systems with systems having little or no history of outdoor exposure. These new coatings systems often require improved surface preparations and new application techniques. The quality and protection resulting from these changes must be determined, increasing the need for quick, reliable, durability assessment procedures. Long-term, outdoor exposure tests cannot meet this need due to the length of time required for obtaining results. The need can be met through the development of reliable short-term evaluation procedures.

1.2 OBJECTIVES

The purpose of the overall study is to aid the Federal Highway Administration in evaluating and selecting protective coatings for use on steel by identifying or developing improved short-term test procedures.

The study was divided into two phases having the following generalized objectives:

1. To evaluate the validity and reproducibility of existing short-term tests for predicting the service life of coatings on steel;

2. To develop, where needed, improved short-term tests; and

1

3. To develop, based upon the improved test methods, a guide
   for evaluating and selecting protective coatings for steel.

Phase I of the study, which is summarized in this report, addresses the
following:

1. Development and justification of a set of criteria for evaluating
   the adequacy of accelerated aging tests for coating systems;

2. Review of currently used accelerated aging procedures;

3. Assessment of these procedures relative to the proposed criteria;
   and

4. Propose research needed for developing improved accelerated aging
   test procedures capable of satisfying the proposed criteria.

2.   ASSESSMENT CRITERIA FOR SHORT-TERM ACCELERATED AGING TESTS

Accelerated aging tests serve two functions. For a particular end-use applica-
tion, users of coatings employ them in making decisions between different coat-
ing systems. Manufacturers of coatings, on the other hand, use them in making
decisions aimed at developing more durable coating formulations. The extent to
which accelerated aging test results are useful in making these decisions depends,
to a large degree, on the criteria used in setting up the experiment. Prior to
large scale testing, therefore, it is important to state the set of criteria
used in developing an accelerated aging test and in assessing the results.

In the process of reviewing these criteria, two sets were identified. The
first is termed the proposed set. It is the set of criteria that the authors
feel best insure that the maximum benefit is derived from the accelerated aging
program. These criteria are currently used or are being considered as the
basis for accelerated aging tests in many industries [4,5,6,7,8,9]. The second
set of criteria more closely reflects the ones currently used in the coating
industry. This is the set against which the short-term tests in section 3 are
assessed. In the recommendations section of this paper, it is proposed that
future accelerated aging tests be developed on the basis of the first set of
criteria.

2.1 PROPOSED CRITERIA FOR ASSESSING COATING SHORT-TERM ACCELERATED AGING TESTS

Short-term tests should 1) provide results which aid in making quantitative
service life predictions under service conditions; 2) be capable of distinguishing
between the durability performances of two or more coating systems under all
environments, and 3) provide a means for monitoring modifications in a coating
system performance because of changes in formulation, surface preparation, etc.
In order to meet these expectations, the following criteria are proposed:

  • PREDICTABILITY - Accelerated aging procedures should provide quan-
    titative service life predictions for the coating at its expected
    environmental operating conditions (see Appendix A).

  • REPRODUCIBILITY - Once an accelerated aging procedure is specified,
    it should be reproducible and provide methods for testing for
    reproducibility.

  • DISTINGUISHABILITY - The procedure should provide a methodology for
    making quantitative comparisons between the performance of different
    coatings. This would be useful in determining the superiority of
    one coating system over another and in ascertaining if improvements
    in the performance of a coating have occurred e.g., due, to changes
    in formulation, surface preparation, application, etc.

  • EXTENDABILITY - The analysis procedure should allow for more than
    one stress type. This should provide more realistic service life
    predictions, permit sensitivity analyses to be made on the effect
    of each stress type, and provide an opportunity for examining
    stress interactions.

3

One theoretical approach capable of satisfying these criteria is presented in Appendix A.

2.2 CRITERIA FOR ASSESSING CURRENTLY AVAILABLE SHORT-TERM ACCELERATED AGING TESTS

After reviewing the literature and after talking with personnel at many different coating laboratories, it became apparent that the criteria stated in section 2.1 are not applicable for assessing currently available accelerated aging tests. Current accelerated aging tests were developed using the concept of a "comparison" test as opposed to "predictability" tests (section 2.1). In comparison tests, specimens from multiple different coating systems are subjected to the same accelerated and outdoor test environments. The coating systems in both the accelerated and outdoor tests are then ranked. A good accelerated aging test is one in which the ranking is similar in both the accelerated and outdoor exposures. For a new coating system, the expected life is measured against control coatings exposed to the same environment. Control coatings are coatings having a known track record.

Comparison tests differ from predictability tests, therefore, in several key ways. First, predictability should be replaced with the term correlatability, since the measure of agreement is one of association. Reproducibility has the same meaning in both contexts; but distinguishability has a more qualitative meaning since coating systems are ranked relative to each other. In comparison testing, the term extendability has little meaning, since the objective is to develop an accelerated test good for all outdoor environments.

3. REVIEW OF ACCELERATED AGING TESTS

A successful durability procedure has two essential components: 1) an accel-
erated aging test procedure, and 2) a measurement procedure for monitoring
material degradation. This chapter focuses upon currently used accelerated
aging procedures. Degradation measurement techniques are reviewed in chapter
4.

3.1 SALT SPRAY

3.1.1 Description

The salt spray test [19] was originally designed to test the durability of
metallic coatings exposed to ocean spray. Over time, it has evolved as the
most popular accelerated aging test for organic coatings covering metallic
surfaces. Basically this test entails spraying coatings housed in a special
cabinet with a 5 percent sodium chloride solution at 35°C. The procedure is
popular because coating failures usually occur in a short time.

Many variations of this salt spray test exist. Sodium chloride is reported to
be more corrosive than seawater and to produce corrosion products different
from those formed from either seawater or calcium salts [20, 21]. Example of
some variations follow. The British continuous salt spray test (BS 3900 Part
F4-1968) [22] uses a synthetic seawater solution (NaCl, 26.5 g; $MgCl_2$, 2.4 g;
$MgSO_4$, 3.3 g; KCl, 0.73 g; $NaHCO_3$, 0.20 g; NaBr, 0.28 g; $CaCl_2$, 1.1 g; water
to 1000 ml). Other salts are also used to simulate other service environments.
The acetic acid/salt spray test, (ASTM B287-74) [23] specifies a solution of
NaCl and acetic acid (pH 3.1-3.3). The copper-accelerated-acetic-acid-salt
spray test, (CASS test, ASTM B368-68) [24] designates a 5 percent NaCl solution
containing copper (II) chloride acidified with acetic acid.

Harrison [26] utilized 3.25 percent $(NH_4)_2SO_4$ and 0.25 percent NaCl solution in
the salt spray test for simulating an industrial environment. He reports that
his results correlate better with 14 years outdoor exposure than salt spray
data resulting from a 3.5 percent NaCl solution. The ARE salt droplet test
[27] (BS 1391:1952) requires a daily spray of a synthetic sea salt solution
(NaCl, 23 g; $Na_2SO_4 \cdot 10\ H_2O$, 8.9 g; $MgCl \cdot 6H_2O$, 9.8 g; $CaCl_2$, 12 g; in 1 liter
of solution) on coated panels. After spraying, the specimens are covered to
prevent evaporation. In the above tests, temperature is controlled.

3.1.2 Extent of Usage

Salt spray testing is widely used to test coatings for corrosion protection. A
salt spray test is included in nearly all steel coating specifications. Most
industrial laboratories utilize the salt spray testing in evaluating new
formulations.

3.1.3 Time to Failure

Time to failure in the salt spray test depends on many factors: type of steel
(hot or cold rolled), surface preparation, coating (resin and pigment),

thickness of coating, and inclusion or exclusion of a top coat. Testing times for alkyds are typically up to 1000 hours, longer for epoxies, and up to 7 months for inorganic zincs. Comparative performance of different binders in the salt spray test is discussed by Appleman and Campbell [29].

3.1.4 Surface Preparation

Surface preparation is an important factor in obtaining meaningful experimental results. Representatives from industrial laboratories commented that the ranking of coatings after salt spray testing would agree quite well with the ranking of exterior exposures if proper attention were given to surface preparation. The thickness of the coating is also an important factor in establishing reliable results in the salt fog test. A critical film thickness of 2.0 mils (50 μm) is indicated in the PACE study [31] and in work reported by Desea [39]. ASTM D609-73 [29] covers procedures to be followed in the preparation of steel panels. ASTM D1014-66 [30] describes methods to minimize the influence of variations in steel surfaces on any series of tests.

Surface preparation depends on the type of substrate to be coated. Both cold and hot rolled steel panels are used [31, 32, 33, 34]. Solvent cleaned cold rolled steel is justified when cold rolled steel is the substrate to be coated. Cold rolled steel panels are readily available and quite uniform. Hot rolled steel should be used, however, when coatings are to be applied to structural steel, since structured steel is hot rolled. Hot rolled steel panels typically have non-uniform surfaces. Both blast and hand cleaned hot rolled steel panels were used in the PACE study [31]. Hospadaruk [38], et al., suggested a large variation in salt spray performance of coated steel was due to carbonaceous residues. Their report shows that failure in a 240 hour salt spray test correlates strongly with high surface carbon concentration, substantiating the need for controlling steel surface cleanliness.

Surface preparation is similar for all the accelerated tests discussed in this chapter. Any requirements particular to an accelerated test will be discussed in connection with that accelerated test.

3.1.5 Modes of Failure

A scribe mark (ASTM D1654-79a) [40] is frequently made through the cured coating prior to testing.

Failures appear as undercutting at the scribe, rusting, and to some extent blistering. Excess amounts of chloride can act to depassivate the surface interfering with inhibitive pigment performance. The availability of an electrolyte permits sacrificial coatings (e.g., zinc rich coatings) to effectively protect the substrate, but at the same time a less protective film may be formed by the reaction products. A difference in zinc reaction products between salt spray testing and exterior exposure has been observed microscopically [41].

3.1.6 Properties Measured

Following salt spray exposure, panels are visually inspected for corrosion, blistering, and undercutting. ASTM standards (D610-68, rusting and ASTM D714, blistering [28]) are available for these properties. The NACE Technical Practice Committee T-6 reports that the above ASTM methods are sufficiently standardized to provide meaningful results. Besides visual ratings, other evaluative procedures are sometimes used after salt spray testing. These include adhesion testing, identification of corrosion products under the film by energy dispersive X-ray, microscopic inspection, and weight change of the panel.

3.1.7 Assessment

Results of salt spray testing are very sensitive to operating conditions. Variables that must be carefully controlled include uniformity of the environment throughout the cabinet, angle of the panels with respect to the vertical, nozzle design, atomization pressure, humidity of the air used for atomization, pH, purity of salt solution, and specimen collection rate [42]. Variations in these operating conditions among cabinets can account for poor reproducibility. Stone [43] reported a coefficient of variation (standard deviation/mean) between 0.1 to 0.3 for three primers. More definite information will soon be available from a committee of the National Association of Corrosion Engineers, which recently conducted an interlaboratory test.

Reports vary as to whether salt spray coating performance results correlate with exterior exposures. Variations in the rankings of coatings exposed to both salt spray environment and exterior environment often occur. Statistical studies aimed at elucidating these variations were not found. Most users look for qualitative agreement between the two exposures or for dramatic reversals. Examples of reversals are cadmium and zinc coatings [44], inorganic and organic zinc primers [45], and several coatings tested in the PACE study [31].

Comments from the authors of the PACE report [31] express the feelings of both users and producers in relation to the salt spray. They concluded that on the whole, "good" paints will usually do well in the salt fog and "poor" paints will usually do poorly, but the exceptions are far too numerous to justify basing decisions solely on salt spray testing methods.

3.2 CYCLIC WEATHERING TESTS

3.2.1 Description

Weathering tests, i.e., carbon or xenon arc or fluorescent lights with humidity, temperature and wetness control, are commonly used to characterize chalking, change in gloss, and change in color for coating systems. Typical cycles [46] are described in ASTM standards D822, D3361-74, G53-77, and G26-77. The development and use of weathering tests was reviewed recently by Ellinger [47].

3.2.2 Extent of Usage

Weathering tests are commonly used for gloss and chalking determinations. Few reports have been made on the use of weathering cycles for the evaluation of coatings for corrosion control; some doubt exists as to whether these tests are good indicators of primer corrosion control [48].

3.2.3 Time to Failure

Exposure times in most weathering cycles, excepting the Dew cycle and fluorescent UV-condensation type (ASTM G53-77) exposure, are from 1000-2000 hours. Dew cycle exposures are often between 50-150 hours. UV-condensation type exposure times depend on the cycle used; typical exposure times fall between 250 to 1000 hours.

In table 1, representative failure times for coatings in several weathering cycles are listed. Failure is designated as a 50 percent loss of gloss. While chalking also occurs during cyclic weathering exposure, quantitative failure times based on extent of chalking were not found in the literature.

3.2.4 Modes of Failure

Little evidence of rusting or blistering is reported after cyclic weathering. Failure is usually reported in terms of the amount of loss of gloss and degree of chalking. Degradation usually results from a combination of ultraviolet light, temperature, and humidity [56]. Chalking occurs if a binder is degraded, thereby, releasing pigment.

3.2.5 Properties Measured

Panels are examined for loss of gloss, color change, and chalking (ASTM 659-74 for chalking, ASTM 523-78 for gloss, and ASTM D1729-69 (1974) for color change) [57]. Chalking is sometimes determined by weighing panels before and after removal of the chalk. Color change can be measured spectrophotometrically.

Lindberg [54] examined the surfaces of several systems (including epoxy, acrylic, polyurethane, and fluoropolymer) using scanning electron microscopy after several hundred hours cyclic weathering exposure and several months outdoor Florida exposure. He also made gloss (ASTM D522) and loss of weight measurements. He concluded gloss measurement is not a good indicator of resin degradation and that gloss measurements should be supplemented with weight loss measurements.

3.2.6 Assessment

The reproducibility of these tests could not be ascertained. Papenroth [58] has shown that variations in UV irradiance in a weathering machine cause differences in chalking and change of gloss. The ranking of panels exposed in accelerated weathering cycles and outdoor environments often differ [49, 53, 54]. However, some researchers have reported good correlation [49-54].

Table 1. Observed Times to Failure[a] in Weathering Machines

Resin	Twin Carbon Arc	Dew Cycle	Xenon Arc 40-45% RH	UV cond.
alkyd	300-2000 hrs[c,d,f,g]	75[d,g]	200-500[f]	240[b]
epoxy	400-2000 hrs[c,d]	50-200[d,g]	400-600[d]	
polyurethane	1000- > 2000 hrs[c]	50-90[c,d]	> 1200[c]	
acrylic (thermosetting)	600- > 1000 hrs[c,f,g]	35-200[g]	400-1000[c]	740[b]
vinyl, chlorinated rubber	> 700 hrs[f]	200[d]	200-300[d,f]	

[a] failure defined as 50 percent loss in gloss

[b] Ellinger, N., J. Oil Col. Chem. Assoc., 62, 136 (1979) [49].

[c] Hoey, et al., J. Oil Col. Chem. Assoc., 57, 151 (1974) [50].

[d] Lindberg, J. J. Oil Col. Chem. Assoc., 58, 399 (1975) [54].

[e] Oakley, E., et al., J. Oil Col. Chem. Assoc., 57, 221 (1974) [52].

[f] Nowacki, L. J., Official Digest, 34, 1191 (1962) [53].

[g] Stanton, J. M., J. of Paint Technology, 39, No. 514, (1967) [55].

3.3 CYCLIC OR SEQUENTIAL TESTS WHICH INCLUDE SALT SPRAY

3.3.1 Description

Specialized tests have been designed which include exposure to salt spray as part of the cycle. The prohesion test described by Timmins [59] includes six periods of alternating salt spray and ambient air drying. The salt spray is Harrison's $(NH_4)_2SO_4-NaCl$ [26] mixture. One major paint company designed its own exposure cabinet in which the samples are exposed to one hour 5 percent salt spray, one hour UV, and a one hour darkness cycle. The Texas Highway Department uses a cycle of 24 hour-heat lamp exposure (60°C black panel temperature) and 48 hour salt spray (20 percent NaCl). The Louisiana Highway Department utilizes an 18 percent salt spray at 67°C for 4 weeks to evaluate coating systems on steel. The Michigan Highway Department has developed a weathering cycle of 200 hours UV-condensation exposure, 50 hours salt spray, and 5 freeze-thaw cycles. Hospadaruk's cycle [38], which accelerates degradation compared to salt spray testing, consists of 0.25 hour immersion in 5 percent NaCl (air saturated), 1.25 hour at room temperature, and 22.5 hours in a humidity cabinet at 49°C and 85 percent relative humidity. Other variations of this test include the above plus a weekly freeze/dry cycle, or dusting the panels with kaolin powder before testing, or a temperature of 60°C in the humidity cabinet.

Tooke's cycle [60] consists of rotating panels in a chamber equipped with ultraviolet lamps and nozzles for spraying synthetic seawater solution [22]. The UV light in Tooke's cycle is on for 40 minutes and off for 40 minutes. Panels are also sprayed for 30 seconds every 15 minutes. Alumbaugh and Hearst [61] developed a cyclic test immersing specimens in aerated synthetic seawater for 1 1/2 hours and drying them in warm air (50°C) for 1 1/2 hours.

Another cyclic test (ASTM D2933-74) [62] combines 4 hours testing in a salt spray, 18 hours at 37.8°C and 100 percent relative humidity and 2 hours in a freezing chamber at -28.3°C. Sakae, et. al. [63] describe several sequences of tests for evaluating corrosion control coatings. These cycles usually include exposure to a carbon arc or xenon arc light, exposure to a salt spray, and exposure to an SO_2 environment. The Port Authority of New York uses a nine step cycle test which includes: 1) 168 hours in a xenon arc accelerated weathering machine, 2) 15 freeze/thaw cycles, 3) 16.5 hours salt fog, 4) 72 hours accelerated weathering, 5) 15 freeze/thaw cycles, 6) 5.5 hours salt fog, 7) 120 hours accelerated weathering, 8) 5.5 hours salt fog, and 9) 120 hours accelerated weathering. They report being able to distinguish some performance differences not distinguishable with salt spray.

3.3.2 Extent of Usage

Most of these tests are relatively new and not standardized; usage is very limited.

3.3.3 Time to Failure

In the prohesion test, primers are tested for 48 hours; complete systems are tested for 2000 hours [59]. In Tooke's [60] accelerated environment, alkyd primers usually failed (ASTM scribe rating of 5) between 400 and 1000 hours. Hospadaruk et al. [38] report their cycle with kaolin dust caused failure (25 percent surface rust) in 600 hours for a maleinized oil primer and in 2000 hours for an epoxy primer. Alumbaugh and Hearst [61] report vinyls and epoxies failed in their test cycle between 700 and 4500 hours. In the Michigan Department of Transportation, cyclic test coatings are typicaly exposed for 300 hours.

3.3.4 Modes of Failure

Since some of the cycles described in this section include ambient environmental exposure, as well as exposure to high humidity, light, and variable of temperature, many failure modes are observed. Typical failures include blistering, rusting, undercutting at the scribe, chalking, and loss of gloss.

3.3.5 Properties Measured

Properties measured after sequential testing are similar to those measured after salt spray and cyclic testing. Coatings and substrates are evaluated for indication of rusting, blistering, flaking, undercutting at the scribe, chalking, and loss of gloss.

3.3.6 Assessment

No specific information pertaining to the assessment is available for this or the following tests. The previously made comments about lack of information on reproducibility and correlatibility apply here and to the following accelerated tests.

3.4 CONDENSATION TESTS

3.4.1 Description

In this test, specimens are exposed to 100 percent relative humidity at a constant temperature. This is often done by exposing the coated side of a test specimen to warm, moist air while keeping the back side of the panel at ambient temperature. Condensation must cover the coatings at all times. Corrosion is dependent on the time of wetness [65]. The temperature prescribed in ASTM D2247-68 (1973) [66] is $38 \pm 1°C$. Sometimes temperatures of $49°C$ or $60°C$ are used [38, 67]. Increasing the temperature from $49°C$ to $60°C$ increases the rate of corrosion 150 to 200 percent [38].

Van Laar [68] varied the humidity test by making the atmosphere rich in HCl, H_2SO_4, or CH_3COOH along with high humidity and elevated temperatures. The HCl atmosphere was the most corrosive, followed by H_2SO_4 and CH_3COOH.

3.4.2 Extent of Usage

This test is frequently used by industrial laboratories for testing coatings for corrosion protection. Several highway departments use a humidity testing method as part of their evaluation procedures. One highway department places coated panels in a concrete curing chamber at a high humidity (95 percent) and elevated temperature 65°C for 300 hours.

3.4.3 Time to Failure

For high build vinyl coatings, Pila [33] found no blistering or corrosion after 800 hours humidity exposure for most pigments tested. Geld [69] reported slight surface deterioration for vinyl or coal tar coatings after 1400 hours of room temperature exposure to 100 percent humidity. However, considerable rusting of substrate surfaces was found after the coating was removed. Several experimental acrylic and alkyd thermosetting coatings failed in 300 to 400 hours [70]. A coal tar epoxy was found to protect the substrate for 1000 hours [71].

3.4.4 Modes of Failure

The conditions in a humidity cabinet are favorable for water permeation, leaching of soluble components, softening, and swelling of coatings. Diffusion of water through coatings occurs rapidly. This reaction is driven osmotically by the presence of soluble components at the coating/substrate interface. Soluble components include contamination present before coating application, diffusion of ions or gases which diffused through the coating, and trapped solvent. The presence of those contaminants can lead to blister formation and rusting.

3.4.5 Properties Measured

The specimens are usually evaluated using ASTM procedures for blistering and rusting. Additional information can be obtained if the coating is removed after testing and the substrate examined.

3.5 IMMERSION

3.5.1 Description

An immersion test for organic coatings on structural steel is described in ASTM D870-54 (1973) [73]. The test specimens are partially immersed in the test liquid (i.e., distilled water, salt solution, acid, base, etc.) and maintained at a temperature of $37.8 \pm 1°C$. The test liquid is changed as required to avoid contamination. Temperature is often a variable.

3.5.2 Extent of Usage

Immersion testing is conducted on coatings that will be subjected to immersion in service.

3.5.3 Time to Failure

Some experimental one-pack epoxy primers immersed in distilled water started
blistering in less than 150 hours. However, rusting occurred only after 150
hours [32]. Two-pack epoxy primers protected the steel substrate for over
2000 hours. Vinyl coating systems showed no rusting after 6190 hours [31].
Linseed oil and linseed oil alkyd coatings have also been reported to show
little blistering after 350 hours [71]. Some phenolic and two-part epoxy
coatings showed little rusting or blistering after 600 hours [32]. Vinyl
coatings showed no blistering after 5700 hours immersion in seawater [31].

3.5.4 Modes of Failure

The modes of failure of coatings due to immersion are similar to those in the
humidity cabinet. Water permeates the coating causing swelling, leaching of
soluble components, and loss of adhesion. Rusting is probably controlled by
the availability of oxygen.

3.5.5 Properties Measured

As with corrosion tests, coatings are examined for blistering and corrosion.
Sometimes coatings are stripped so that the substrate can be examined. Tooke
and Montalvo [74] followed the loss of adhesion as a function of time of immer-
sion. Adhesion for all primers studied (oil, oil alkyd, alkyd, and melamine
alkyd) fell off rapidly with immersion time.

3.6 KESTERNICH TEST

3.6.1 Description

This test was designed to simulate weathering in industrial environments. The
stresses include elevated temperature, 100 percent relative humidity and SO_2.
The Kesternich test cycle is described in standard DIN 50018 [75]. Samples
are placed in a cabinet in which water and SO_2 are introduced and the cabinet
is heated to a 40°C. After eight hours of exposure, the door of the cabinet
is opened and the specimens are exposed to room conditions for 16 hours.

3.6.2 Extent of Usage

Although often reported in the European literature [76, 77], the test is not
widely used in the United States.

3.6.3 Time to Failure

Kesternich testing is usually conducted for 240 to 1000 hours. At the end
of the exposure time, the panels are evaluated. After 240 hours, Chess [76]
reported that coatings on galvanized steel showed partial to total
deterioration.

13

3.6.4 Modes of Failure

It has been shown that SO_2 permeates free paint films [12]. It is, therefore, possible that ions may be formed at the coating/substrate interface by the reaction of water and oxidizers with SO_2. Chemically, ions on the metal surface would cause an increase in osmotic pressure and interfere with passivating properties of inhibitive pigments, thus promoting corrosion.

3.6.5 Properties Measured

As with the salt fog test, panels are evaluated for blistering, rusting, and undercutting of the coating at the scribe or edge.

3.7 CATHODIC TEST

3.7.1 Description

Cathodic tests, often called "bullet hole" tests [78], are designed to test the protective qualities of sacrificial coatings. The test specimens are prepared in such a way as to leave an uncoated circular or rectangular area in the center of the panel. Exposed edges of the panel are frequently coated with wax to prevent corrosion. The specimen is then immersed in a liquid (such as synthetic seawater or 3 percent NaCl) at room temperature until corrosion is observed in the uncoated area, the "bullet hole." For zinc rich coatings, the zinc becomes the anode, while the exposed steel substrate becomes the cathode. As long as an anodic reaction does not occur on the steel surface, corrosion is prevented.

3.7.2 Extent of Usage

This test is sometimes used by coating manufacturers to assess the ability of sacrificial coatings to provide cathodic protection. It is to be included in specifications developed by the Navy and is being used in the evaluation of zinc rich coating extenders.

3.7.3 Time to Failure

These tests are usually carried out until corrosion occurs in the "bullet hole." The varying specification requires that coatings shall prevent corrosion in the base metal area for a minimum of 30 days immersion in synthetic seawater.

3.7.4 Modes of Failure

Failure occurs when the zinc is consumed. The steel substrate then becomes anodic and rusting occurs. This test does not take into account the protective coating formed by the zinc reaction products.

3.7.5 Properties Measured

Only the time for rust to appear in the "bullet hole" is measured.

4. MEASUREMENT TECHNIQUES FOR EARLY CHARACTERIZATION OF DEGRADATION

The accelerated test methods described in chapter 3 have many shortcomings. One of the most significant is that the relationship between performance in the accelerated weathering environment and service environment is not well defined. Currently, more sensitive evaluation techniques are being developed. These techniques include measures of adhesion, electrical properties, permeabilities, mechanical stress, and chemical changes.

4.1 ADHESION

4.1.1 Significance of Property

Since it is thought that corrosion does not proceed to any extent as long as the coating adheres firmly to the substrate [12, 18], changes in adhesion should relate to durability. However, these measurements must be done carefully and under controlled conditions as adhesion of coatings to a substrate depends on environmental conditions [85]. Adhesive strength usually decreases when coatings are in a humid or wet environment [81, 82] and recovers to some extent after the coatings are placed in a dry environment [86]. The ability of a coating to maintain good adhesive properties under wet conditions is thought to be very important with respect to its ability to provide corrosion protection [12].

4.1.2 Measuring Techniques

Bullett and Prosser [87] have recently reviewed the available adhesion measuring techniques. Among these, two are ASTM standard test methods -- ASTM D2197 and 3359. ASTM D2197-68 (reapproved 1979) [88] covers the determination of adhesion by a scrape tester method or by a parallel groove adhesion tester. In the scrape tester method, adhesion is determined by pushing the coated panels beneath a rounded stylus or loop which is loaded in increasing amounts until the coating is sheared from the substrate surface. ASTM's precision statement says that the results agree well with other qualitative evaluation methods. In the parallel groove method, adhesion is evaluated in terms of the closeness with which parallel grooves can be cut through the coating before the intervening film is lifted from its substrate. ASTM's statement of precision says that 95 percent of the time the same operator should be within two microknife adhesion units for duplicate tests; measurements made by different operators in different laboratories should be within four units.

Tape test methods (ASTM 3358 [89]) are commonly used in the industry for measuring adhesion. In one, an x-cut is made through the coating over which a pressure sensitive tape is applied and removed; adhesion is assessed qualitatively on a scale of zero to five. In the other method, a matrix pattern, using six or seven cuts in each direction is made through the film. Pressure sensitive tape is applied over the matrix and removed. Adhesion is evaluated by comparison with descriptions and illustrations on a zero to five scale. Both methods are repeatable to within one rating and reproducible to within two ratings at the 95 percent confidence level, according to the ASTM statement of precision.

The most commonly used measure of adhesion, which gives a measure of the force needed to remove a coating, is a tensile or pull-off method. Standard methods for pulloff adhesion tests are described in ISO 4624-1978 (E) [90] and DIN 53232 [91]. In both standard test methods, two different test assemblies are described. In one test, a coating is applied to the top of a rigid cylinder (approximately 1 cm in diameter) to which a second cylinder of the same size is adhered. In the other test, a rigid cylinder is glued to a coated panel having greater dimensions than the cross-sectional area of the cylinder. The amount of force needed to pull the test assemblies apart is measured and the mode of failure is noted. For both procedures, results are invariant with cylinder diameter ranging from .6 to 2.5 cm.

For these two tests, the stress distributions are different [92]. Edge effects in the second test contribute to an apparent lower adhesion value and to a greater experimental variation.

The Joint Service Research and Development Committee on Paints and Varnishes [93] sponsored an extensive study carried out to investigate the direct pull-off techniques. Surface preparation, paint application, and temperature were factors affecting interlaboratory reproducibility. Proper alignment and rate of loading also affect variability. Sickfield [92] reports a range of 5 to 15 percent from the mean for coatings tested between two cylinders and a range of 10 to 30 percent of the mean when the cylinder is glued to a panel. Others report similar variations in test results [94].

Two field tensile testers are the Elcometer[1] and the torque wrench. The Elcometer exerts a tensile stress through the action of a spring. Experimental results for this tester often display high variations. The torque wrench or spanner method involves gluing a rigid test cylinder to the coating and measuring the torque necessary to remove it [95]. Breaking strength values for both procedures are of the same order of magnitude and have similar failure characteristics.

4.2 ELECTRICAL MEASUREMENTS

4.2.1 Significance of Property

Electric properties relate to the corrosion protective qualities of the coatings. Some correlation between corrosion protection qualities of the coatings and electrical properties has been found. Limited information on the mechanism of corrosion of a coating during immersion can be obtained from electrical measurements [102]. Leidheiser [96] recently reviewed electrical measurement procedures.

---

[1] Elcometer is a brand name adhesion tester. Recognition of a specific commercial product is not meant to constitute an endorsement by the National Bureau of Standards.

4.2.2 Measuring Techniques

4.2.2.1 D. C. Resistance Measurements

Bacon et. al., [97] measured D. C. resistance of over 300 organic coatings on metal substrates immersed in electrolytes over a period of 150 days. In cases of good protection (determined visually), the resistance of the film exceeded 10^8 ohms/cm^2. When corrosion occurred, the resistance was less than 10^6 ohms/cm^2. Coatings having resistances between 10^6 and 10^8 ohms/cm^2 were sometimes good and sometimes not.

Mayne and Mills [98] demonstrated that the electrical properties of a film vary greatly with location on the film. They found a correlation between film resistance and corrosion. D.C. resistances of films were also shown to change after immersion in KCl [98, 103, 104]. Films increasing in resistance did not corrode, while films decreasing in resistance did. Increased resistance was thought to be associated with increase in cross link density. The authors suggest that improved protection may be obtained by uniformly increasing crosslink density over the film.

Equipment needed to carry out these measurements is described by Brown [105]. Included is a calomel or Ag/AgCl electrode, an electrometer with a high input resistance, and two potentiometers to provide added potential for high resistance measurements or to charge panels having a long time constant.

4.2.2.2 A. C. Resistance Measurements

A.C. resistance measurements can provide the same information as that obtained from D.C. measurements. In addition, A.C. measurements have several advantages over D.C. measurements. The most important one is the ability of measurements to be made as a function of frequency. Processes occuring in the coating can be distinguished from those at the interface by obtaining data over a wide range of frequencies [107, 108].

4.2.2.3 Capacitance Measurements

Changes in the capacitance of coatings have been associated with the penetration of water into the film. Difference in water uptake, determined gravimetrically and by capacitance measurements, has been used to characterize differences in the mode of distribution of water in coatings as a function of pigment and polymer [111]. Models have been developed relating change in capacitance with change in depth of penetration of water into the coating [102, 112].

4.3 PERMEABILITY MEASUREMENTS

4.3.1 Significance of Property

Since water, oxygen, and ions are needed at the coating/substrate interface for corrosion to occur, the rate at which they permeate would seem to be related to the protective qualities of the coating. A great amount of work has recently been done to measure permeabilities of different coating systems to do the

following: 1) water: as a function of relative humidity and temperature [113, 114]; 2) oxygen: as a function of temperature and the water absorption [115]; 3) sulfur dioxide: as a function of temperature [12]; and 4) various ions: [116, 117, 118, 119, 120].

It is generally agreed that the water permeation rate through a coating does not control the corrosion rate [12]. The rate of oxygen permeation is often a sizeable fraction of that needed for corrosion of unprotected mild steel [18, 115]; however, corrosion of coated steel, at least in the early stages of exposure, proceeds much slower. These ideas suggest that permeabilities to water and oxygen are linked with other protective mechanisms.

The permeability of coatings to ions such as Cl^-, SO_4^{-2}, and Na^+ are several orders of magnitude smaller than to water [12, 121]. Evidence exists that ion permeability and ion exchange properties of the coating may be related directly to the protective quality of the paint [118, 122, 123].

4.3.2 Measuring Techniques

Free films are used in obtaining measurements of permeability to oxygen and water.

Oxygen permeabilities can be determined using a pressure differential method. The free coating film of interest is positioned between a large and a small chamber. The large chamber contains oxygen at a pressure of 50 or 100 mm of mercury (6.5×10^3 to 13×10^3 Pa), while the small chamber is evacuated. Pressure rises are then measured. For nine different films, oxygen permeability was insensitive to relative humidity but very sensitive to temperature [115].

Sulfur dioxide permeabilities are measured by exposing one side of the film to humid air containing SO_2 and titrating the water leaving the film on the downstream side of the permeation cell for its acid content [12].

The measurement of ion permeabilities and ion exchange properties of films is much more difficult. Recent work by Ruggeri and Beck [121] identifies problems associated with measurements for films with very low permeabilities and ion concentrations. Typical experimental procedures include radioactive tracer methods and use of special electrodes or specific ion titrations. These measurements are not routinely done for organic coatings.

4.4 MECHANICAL STRESS MEASUREMENTS

4.4.1 Significance of Property

Internal stresses of coatings have a strong influence on many physical and chemical properties of coating systems. Stresses arise during curing of the film because of shrinkage and crosslinking [124].

Changes in temperature and relative humidity cause changes in the internal stress. .The thermal expansion coefficients of some coatings are on the order of two to three times greater than that of metals. Hence, temperature

18

decreases will increase film stress. If the additional stress is sufficiently high, the film can either become detached from the substrate or crack [129]. Water may also act as a plasticizer reducing the internal stress [126]. It can also leach out soluble products, which may result in increased internal stress in the film on redrying [125].

4.4.2 Measuring Techniques

4.4.2.1 Fixed Film

Internal stresses in coatings can be determined using a cantilever beam deflection method. A coating is applied to one side of a thin steel strip and deflection is measured microscopically [127] or mechanically [128] as the coating cures. Saarnak [127] reports that, if measurement procedures and environmental conditions are carefully controlled, satisfactory reproduction is possible. Croll [128] reports experimental errors of about 15 percent. Internal stresses of 5 MPa have been reported for freshly cured coatings.

4.4.2.2 Free Films

Mechanical properties of free films can be determined by stress-strain measurements, transient, and dynamic tests. In one type of dynamic test, an oscillating strain is applied at a constant frequency and the resulting stress and phase difference measured. Measures of both elastic and viscous response are obtained. When these tests are performed as a function of temperature, glass transition temperatures and brittle-ductile transition temperatures [130] are obtained. Loss tangent curves obtained from dynamic testing are related to impact resistance of the film.

Changes in mechanical properties after aging can often be related to coating durability [131]. Talen [132] found that alkyd resin varnish tensile results correlated well with outdoor durability. Tensile tests after outdoor exposure also revealed changes in properties sooner than visual changes.

4.5 CHEMICAL TECHNIQUES

4.5.1 Significance of Properties Measured

In order to improve coating systems, it is necessary to link changes in the coating microstructure to macrostructural performance changes. By making this connection, it is hoped that the causes of coating system degradation may be readily identified; thus, this would provide information for coating systems improvement. Analytical equipment capable of making microstructural change characterizations are described below.

4.5.2 Measuring Techniques

4.5.2.1 Ellipsometry

Ellipsometry is an optical technique which has been used for observing changes under transparent coatings at the coating/substrate interface. An

19

ellipsometer detects phase and amplitude changes in visible elliptically polarized light when it is reflected from the metal surface. The changes can be related to the metal oxide film thickness. This technique had previously been applied to the study of corrosion of metals immersed in a solvent [133]. Film formation, film dissolution, and surface roughening were observed.

When electrochemical measurements are carried out simultaneously with the optical measurements, changes in electrical potential, and pH can be determined while observing changes in metal oxide film thickness. Ritter [134] used this technique to study iron coated with a transparent cellulose nitrate coating and with various inhibitors either in or under the coating. At least two stages of activity were noted during immersion in 0.05N NaCl. During the first stage, oxygen, water, and Cl$^-$ permeated the coating causing localized breakdown of the oxide layer originally present on the metal surface. Active metal sites were exposed and became anodic areas while less active areas became cathodic areas and the pH increased gradually. During the second stage, a large decrease in one of the ellisopmetry parameters was noted as the pH increased. This appeared to be due to both oxide film growth and surface roughening corresponding to active corrosion. Both the detection of corrosion and the kinetics of the reactions can be determined with this technique. This technique may be useful in evaluating the performance of inhibitors as well as surface preparation methods and pretreatments.

4.5.2.2 X-Ray Photoelectron Spectroscopy

X-ray photoelectron spectroscopy has been used to identify modes of failure at the coating/substrate interface [80, 135, 136] as well as to characterize surfaces of substrates before application of a coating [80]. For example, examination of the surfaces after cathodic disbondment has shown that saponified primer coating was present on the metal substrate [136]. Hence, failure was described as cohesive since some polymer remained on the surface.

These techniques appear to be very powerful in examining the metal surface and the metal/coating interface. The instruments are expensive and technical knowledge and skill is required for using these instruments, designing experiments, and analyzing the results.

4.5.2.3 Infrared Spectroscopy

Infrared spectroscopy is used to examine the top surface of coatings. Hearst [137] examined the surfaces of several kinds of coatings before and after atmospheric, xenon-arc, and mercury-arc weathering using a dispersive infrared spectrophotometer. The effect of exposures on the coatings was an increase in carbonyl content. However, the changes he observed in the surface did not correspond to durability in service. This is not completely unexpected since it is generally felt that changes in the surface of coatings do not influence performance unless the coating becomes very thin.

Very small differences in chemical composition can be determined using a Fourier transform infrared spectrophotometer. It is possible to determine the combined or individual effect of both heat and moisture on coatings by subtracting spectra. It is also possible to obtain spectra at varying depths from the surface and observe the changes in composition as a function of depth. The potential of this instrument is very great.

5. SUMMARY AND CONCLUSIONS

Prior to reviewing the literature, four criteria were established for evaluating accelerated aging tests for coatings over steel substrates. The four criteria were predictability, reproducibility, distinguishability, and extendability; it was felt, at the time, all accelerated aging tests should satisfy these criteria. After a cursory review of the literature, it became apparent however, that these are not the criteria upon which currently used accelerated aging tests were based. The predominant philosophy of current procedures is that of association or correlatability as opposed to predictability. Tests based on correlatability are termed comparison tests.

The most common comparison tests found in the literature and reported by coating laboratories were the salt fog, cyclic or sequential weathering, high relative humidity, cathodic, and the Kesternich tests. The salt fog is the most frequently used. Although the stress conditions in the above vary from test to test, a certain commonality exists. Each of these tests is designed to subject the coatings to a set of stresses or a sequence of stresses thought to be similar to those encountered in service. Typically, multiple coatings are subjected to a test and some of these coatings are controls (controls are coatings having whose durabilities are well known). After exposure to the test conditions, the performance of each coating is assessed and ranked against that of the controls. Correlations are then made relating the accelerated test rankings against those of the same coatings exposed outdoors.

In assessing these comparison tests, several serious problems have been noted. First, results from the analysis are measures of association, not quantitative service life predictions. This makes it difficult to distinguish between the merits of different coatings, makes the results difficult to extend to other possible service environments, and requires reliable long-term performance data for the control coatings. Second, the rankings from different iterations of the same accelerated aging tests are seldom reproducible. Finally, poor correlations exist between accelerated and outdoor exposure data. The end result of these deficiencies is that users and manufacturers of coating systems tend not to rely on the results of their short-term tests; instead, they depend heavily upon long-term outdoor exposure results and use their short-term results as supporting evidence. The obvious result of this lack of confidence is that the qualification times for new coatings are very long.

In conclusion, existing short-term test methods do not satisfy the four criteria outlined in chapter 2. Consequently, the methods are not fully adequate for reliably predicting service life of coatings.

6. RECOMMENDATIONS

The ultimate objectives of any accelerated aging procedure are to form the basis for the selection of the best coating for a given environmental and operating condition and to provide a method for assessing durability improvement for a coating system. These objectives can best be met if quantitative service life predictions can be made from the short-term or accelerated test data. It has been concluded that current short-term tests do not meet the need for quantitative service life data and that accelerated aging procedures having a more scientific base are needed. Specifically, we recommend:

1. Use of accelerated test procedures in which stresses are varied singly, but at multiple levels; e.g., exposing specimens to 95 percent relative humidity at each of four temperature levels -- 30°C, 50°C, 70°C, and 90°C. Initially, the response of the coatings to constant stress conditions should be accessed. Once this is accomplished, cyclic changes in a stress should be examined.

2. Application of analytical tools for quantitative characterization of the materials and material degradation processes as a function of exposure time. Included in this are non-destructive evaluation procedures useful in quantifying coating degradation.

3. Application of mathematical methods capable of relating material response to a wide variety of environmental and operating conditions. Reliability theory, as outlined in Appendix A, seems suitable.

7. REFERENCES

1. Frondistou-Yannas, S., "Coating and Corrosion Costs of Highway Structural Steel," Federal Highway Administration Report No. FHWA-RD-79-121, 1980.

2. Mann, N. R., Shafer, R. E., and Singpurwalla, N. D., Methods for Statistical Analysis of Reliability and Life Data, John Wiley, 1974.

3. Bain, L. J., Statistical Analysis of Reliability and Life Testing Models: Theory and Methods, Marcel-Dekker, 1978.

4. Lieblein, J. and Zelen, M., "Statistical Investigation of the Fatigue Life of Deep Groove Ball Bearing," Res. Paper 2719. J. Res. Nat. Bur. Stand., 57, 273 (1956).

5. Nelson, W., "Accelerate Life Testing -- Step Stress Models and Data Analyses," IEEE Trans. Reliability R-19, 103 (1980).

6. Shooman, M. L., Probabilistic Reliability: An Engineering Approach, McGraw-Hill, New York, 1968.

7. Whittaker, I. C. and Besumer, P. M., "A Reliability Analysis Approach to Fatigue Life Variability of Aircraft Structures," Boeing Comp. Tech. Rep., AFMC-TR-G9-65, 1969.

8. Cinlar, E. and Bazant, Z. P., "Stochastic Process for Extrapolating Concrete Creep," Journal of the Engineering Mechanics Division, ASCE, 1069-1088 (1977).

9. Martin, J. W., "The Analysis of Life Data for Wood in the Bending Mode," Wood Science and Technology, 14, 187 (1980).

10. Hare, C. H., "Anti-Corrosive Barrier and Inhibitive Primers," Federation Series on Coatings Technology, Unit 27, Federation of Societies for Coatings Technology, 1979.

11. Yassen, M., and Funke, W., "Effect of Temperature on Water Adsorption and Permeation Properties of Coatings," J. Oil Col. Chem. Assoc., 62, 284 (1979).

12. Funke, W., "Corrosion Tests for Organic Coatings - A Review of Their Usefulness and Limitations," J. Oil Col. Chem. Assoc., 62, 63 (1979).

13. Walker, P., "The Effect of Water Upon the Adhesion of Surface Coatings," Paint Technology, 31, No. 8, 22 (1967).

14. McCafferty, E., "Mechanisms of Corrosion Control by Inhibitors," Corrosion Control by Coatings, Leidheiser H., ed., p. 276, Science Press, Princeton, 1979.

15. Stern, M., "The Mechanism of Passivating-type Inhibitors," J. Electrochem Soc., 105, 638 (1958).

16. Thomas, J. G. N., "Uptake of Phosphate Ions by Oxide Films on Mild Steel," Brit. Corros. J., 5, 41 (1970).

17. Lumsden, J. B., "The Properties of Passive Films on Metals," p. 173 in Corrosion Control by Coatings, Leidheiser, H., ed., Science Press, 1979.

18. Mayne, J. E. O., "The Mechanism of the Protective Action of Paints," Corrosion, Vol. 2, 2nd ed., L. L. Sheir, ed., Newnes-Butterworths, London 1976, 15, 24.

19. "Standard Method of Salt Spray (fog) Testing", B117-73 (1979), Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

20. Champion, F. A., Corrosion Testing Procedures, 2nd ed., John Wiley, New York, 1965.

21. Brasher, D. M. and Nurse, T. J., "Electrical Measurements of Immersed Paint Coatings on Metal. II., Effect of Osmotic Pressure and Ionic Concentration of Solution on Paint Breakdown," J. Appl. Chem., 9, 96 (1959).

22. "Resistance to Continuous Salt Spray," BS 3900: Part 4; British Standards Institution, 2 Part Street, London WIA 285, 1968.

23. "Standard Method of Acetic Acid-Salt Spray (fog) Testing," B287-74, Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

24. "Standard Method for Copper-Accelerated Acetic Acid-Salt Spray (fog) Testing (Cass Test)," B368-68, Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

25. "Salt Spray (fog) Test, Method 6061, Federal Test Method Standard No. 141A, Paint, Varnish, Lacquers, and Related Materials; Methods of Inspection, Sampling and Testing," Change Notice 3, July 1976.

26. Harrison, J. B., "The Realistic Prediction of Primer Performance, A Case History," J. Oil Col. Chem. Assoc., 62, 18 (1979).

27. Performance Tests for Protection Schemes Used in the Protection of Light-guage Steel and Wrought Iron Against Corrosion," BS 1391: 1952, British Standards Institute, 2 Part St., London WIA 285, 1960.

28. "Evaluating Degree of Rusting on Painted Steel Surfaces," D610-68 and "Evaluating Degree of Blistering of Paints," D714-56, Part 27, 1980, Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

29. Appleman, B. R. and Campbell, P. G., "Salt Spray Testing for Short-Term Evaluation of Coatings," presented at the Annual Meeting of the Federation of Societies for Coating Technology, Atlanta, GA, October 29, 1980.

30. "Standard Method of Conducting Exterior Exposure Tests of Paints on Steel," D1014-66 (1973), Part 27, Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

31. Bruno, J. A., Keane, J. D., and Weaver, R. E. F., "Performance of Alternate Coatings in the Environment (PACE)." Report FHWA-PA-79-05, May, 1979.

32. Lapasin, R., Papo, A., and Torriano, G., "New Shop Primers for Steel Based on Inhibitive Pigments of Low Toxicity," Br. Corros, J., $\underline{12}$, No. 2, 91, (1977).

33. Pila, S., "Factors Involved in the Formulation of Anti-Corrosive High Build Vinyl Coatings," J. Oil Col. Chem. Assoc., $\underline{56}$, 195 (1973).

34. Boxall, J., Von Fraunhofer, J. A. and Werren, S. C., "Investigation of the Water and Ion Permeation Characteristics of Certain Polymers," J. Oil Col. Chem. Assoc., $\underline{55}$, 24 (1972).

35. Emch, D., "Water Borne, Air Dry, Force Dry, Lead and Chromate-Free Metal Primers," Presentation at May, 1980 Symposium of Baltimore Society for Coatings Technology.

36. Van Westrenen, W. J., "The Behavior in Salt-Spray Exposure of Water-Soluble Epoxy Ester Coatings," Paint Technology, 27, November 1968.

37. Cook, A. R., "Galvanized Steel and Zinc Pigments, Paints," in Corrosion Control by Coatings, Leidheiser, H., ed., Science Press, 1979, p. 49.

38. Hospadaruk, V., Huff, J., Zurilla, R. W. and Greenwood, H. T., "Paint Failure, Steel Surface Quality and Accelerated Corrosion Testing," Society of Automotive Engineers, Technical Paper Series, No. 780186, 1978.

39. Desea, R. I., "Corrosion Resistance of Waterborne Industrial Force Dry and Bake Coatings," Presentation at May, 1980 Symposium of Baltimore Society for Coating Technology.

40. "Standard Evaluation of Painted or Coated Specimen Subjected to Corrosive Environment," D1654-79, Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

41. Newton, D. S. and Guest, B. M., "The Natural and Accelerated Weathering of Fine Dust Primers," J. Oil Col. Chem. Assoc., $\underline{47}$, 942 (1964).

42. Gaynes, N. I., "The Organic Corner, The Salt Fog Test on Organic Coatings," Metal Finishing, $\underline{72}$, No. 7, 41 (1974).

43. Stone, J., "Paint Adhesion on a Scribed Surface: The PASS Test," J. of Paint Technology, 41, No. 539, 661 (1969).

44. Mazia, J., "The Organic Corner, More Metal Finishing Myths (MFM's)," Metal Finishing, 75, No. 5, 77 (1977).

45. Morrison, J., National Aeronautics and Space Administration, John F. Kennedy Space Center, FL., private communication, 1980.

46. a. "Standard Practice for Operating Light-and Water-Exposure Apparatus (Carbon-Arc type) for Testing Paint, Varnish, Lacquer, and Related Products," ASTM D822-79, Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

    b. "Standard Recommended Practice for Operating Light-Exposure Apparatus (Unfiltered Carbon-arc type), for Testing Paint, Varnish, Lacquer and Related Products Using the Dew Cycle," ASTM D3361-74, Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

    c. "Standard Recommended Practice for Operating Light-Exposure Apparatus (Xenon-Arc type) with and without Water for Exposure of Nonmetallic Materials," ASTM G26-77, Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

    d. "Standard Recommended Practice for Operating Light- and Water-Exposure Apparatus (Fluorescent UV-condensation type) for Exposure of Non-metallic Materials," ASTM G53-77, Part 41, 1977 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

47. Ellinger, M., "Weathering Tests," Prog. in Org. Coatings, 5, 21 (1977).

48. McMichael, K. L. and Azar, D., "Thin Films of Paint on Steel," FHWA-LA-77-108, May, 1977.

49. Ellinger, M., "Accelerated Weathering Tests," J. Oil Col. Chem. Assoc., 62, 136 (1979).

50. Hoey, C. E. and Hipwood, H. A., "An Appraisal of Analytical Weathering Methods for Assessment of the Durability of Paint Film," J. Oil. Col. Chem. Assoc., 57, 151 (1974).

51. Berger, W., "Light Stability and Outdoor Resistance of Paint Binders," Paint Manufacture, 30, November, 1972.

52. Oakley, E. and Marron, J. J., "Accelerated Testing of Durable Coating," J. Oil Col. Chem. Assoc., 57, 221 (1974).

53. Nowacki, L. J., "An Evaluation of Various Weatherometers for Determining the Service Life of Organic Coatings," Official Digest 34, 1191, (1962).

54. Lindberg, B., "Theories-Laboratory Investigation-Practical Performance," J. Oil Col. Chem. Assoc. 58, 399 (1975).

55. Stanton, J. M., "Evaluation of the Dew Cycle Method of Accelerated Testing," J. of Paint Technology, 39, No. 514, (1967).

56. Hoffmann, E. and Saracz, A., "Weathering of Paint Film IV: Chalking in Emulsion Paint Films Caused by Silicone-Coated Anatase Titanium Dioxide and Zinc Oxide of Varying Humidities," J. Oil Chem. Assoc. 55, 1079, (1972).

57. Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

   a. "Standard Method of Evaluating Degree of Chalking of Exterior Paints," D659-74.

   b. "Standard Test Method for Specular Gloss," ASTM D523-78.

   c. "Standard Method for Visual Evaluation of Color Differences of Opaque Materials," ASTM D1729-69 (1974).

58. Papenroath, W., Atlas Sunspots, 2, No. 4, 1 (1973).

59. Timmins, F. D., "Avoiding Paint Failures by Prohesion," J. Oil Col. Chem. Assoc., 62, 131 (1979).

60. Tooke, W. R. and Hurst, D. R., "Accelerated Environmental Testing," Georgia Department of Transportation, Project No. 6301, November, 1973.

61. Alumbaugh, R. L. and Hearst, P. J., "Prediction of Paint Performance from a Combination of Accelerated Laboratory Tests," Civil Engineering Laboratory, Tech. Note N-1412, November, 1975.

62. "Standard Method of Testing Coated Steel Specimens Dynamically for Resistance to Corrosion," ASTM D2933-74, Part 27, 1980 Annual book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

63. Sakae, Y., Kikuchi, M. and Najimak, "One Proposal of Accelerated Weathering Tests," Proc. Int. Congr. Met. Corros., 5th, 1044, 1972 (Pub. 1974), Ed. by Sato, N., National Assoc. Corros. Eng., Houston, TX.

64. Burnside, G. L. and Brewer, G. E. F., "Five Year Use, Test Track Run, and Salt Spray Test, Show Excellent Correlation in Automotive Primer Coats," Metal Finishing, 71, No. 11, 62 (1973).

65. Grossman, P. R., "Investigation of Atmospheric Exposure Factors that Determine Time of Wetness of Outdoor Structures," Special Technical Publication 646, American Society for Testing and Materials, Philadelphia, PA, 1978.

66. "Standard Method for Testing Coated Metal Specimen at 100% Relative Humidity," D2247-68 (1973), Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

67. Jedlicka, W. W. and Geschke, T. H., "Rapid and Continuous Evaluation of Corrosion Using Extremity Thin Metal Substrates," J. Paint Technology, 41, 680 (1969).

68. Van Laar, J. A. W., "The Durability of Lacquered Steel at Various Relative Humidities," Paint Technology, 30, No. 12, 36 (1966).

69. Geld, I. and McCaul, C., "Corrosion and Coatings Test Program of the NYC Board of Water Supply," Materials Performance, 11, No. 2, 41 (1972).

70. Wampner, H. L., "Acrylic Resins for Industrial Chemical Coatings," J. Oil Col. Chem. Assoc., 52, 309 (1969).

71. Guruviah, S. and Rajagopalan, K. S., "Evaluation of Primer Paint by Accelerated Test," Paintindia, 19, No. 2, 17 (1969).

72. Mazia, J., "The Organic Corner," Metal Finishing, 77, No. 6, 63 (1979).

73. "Standard Method of Water Immersion Test of Organic Coatings on Steel," ASTM D870-54 (1973), Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

74. Tooke, W. R. and Montalvo, J. R., "Coatings Adherence Measurement by an Angular Scribe-Stripping Technique," J. Paint Technology, 38, 18 (1966).

75. "Method of Test in Damp Heat Alternating Atmosphere Containing Sulphur Dioxide (Kesternich Type Apparatus)," DIN 50018, December, 1963.

76. Chess, J. A., Hastings, M. R. and Paolini, Jr., A., "Accelerated Corrosion Testing," J. Coating Technology, 49, 55 (1977).

77. Leclercq, M., "New Instrumentation for Accelerated Corrosion Tests in a Damp Sulfur Dioxide-Containing Atmosphere," FATIPEC Congress, 14, 371, (1978).

78. Metil, I., "Ferrophosphrous Extenders," Modern Paint and Coatings, October, 1977.

79. Metil, I., "Recent Developments in Organic Zinc-rich Primers," Modern Paint and Coatings, 39, December, 1979.

80. Castle, J. E. and Watts, J. F., "Cathode Disbondment of Well Characterized Steel Interfaces," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August, 1980, p. 252.

81. McGill, W. J., "Adhesion and Failure of Organic Coatings," J. Oil Col. Chem. Assoc., 60, 121 (1977).

82. Kumins, Charles A., "Physical Chemical Models for Organic Protective Coatings," J. Coatings Technology, 52, No. 664, 39 (1980).

83. Bullett, T. R., "Film Structure and Adhesion," J. Adhesion, 4, 73 (1972).

84. Croll, S. G., "Adhesion Loss Due to Internal Strain," J. Coatings Technology, 52, No. 665, 35 (1980).

85. Walker, P., "Long Term Adhesion Studies on Multicoat Systems Exposed to Natural Weathering," J. Oil Col. Chem. Assoc., 52, 516 (1969).

86. Walker, P., "The Effect of Water Upon the Adhesion of Surface Coatings," Paint Technology, 31, No. 8, 22 (1967).

87. Bullett, T. R. and Prosser, J. L., "The Measurement of Adhesion," Prog. in Org. Coatings, 1, 45 (1972).

88. "Standard Test Methods for Adhesion of Organic Coatings," ASTM D2197-68 (1979), Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

89. "Standard Methods for Measuring Adhesion by the Tape Test," ASTM D3359-78, Part 27, 1980 Annual Book of ASTM Standards, American Society for Testing and Materials, Philadelphia, PA.

90. "Paints and Varnishes - Pull-off Test for Adhesion," ISO 4624-1978(E), International Organization for Standardization, 1978.

91. "Messung der Haftfestigkeit von Anstrichen und ahnlichen Beschichtungen nach der Abreissmethode," DIN 53232, April 1973, Alleinverkauf der Normblatter durch Beuth-Vertrieb GmbH, Berlin.

92. Sickfield, J., "Experimental Aspects of Adhesion Testing, An IUPAC Study," J. Oil Col. Chem. Assoc., 61, 292 (1978).

93. Joint Services Research and Development Committee on Paints and Varnishes, "An Investigation into a Method of Test for Assessing the Adhesion of Paint Coatings: Part II," J. Oil Col. Chem. Assoc. 49, 17 (1966).

94. Schwab, L. K. and Drisko, R. W., "Relation of Steel Surface Profile to Coating Performance," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August, 1980.

95. Walker, P., "Factors Affecting the Performance of Etch Primers," Paint Technology, 33, No. 2, 18 (1968).

96. Leidheiser, H., "Electrical and Electrochemical Measurements as Predictors of Corrosion at the Metal-Organic Coating Interface," Progress in Org. Coatings, 7, 79 (1979).

97. Bacon, R. C., Smith, J. J., and Rugg, F. M., "Electrolytic Resistance in Evaluating Protective Merit of Coating on Metals," Ind. Eng. Chem., 40, 161 (1948).

98. Mayne, J. E. O. and Mills, D. J., "The Effect of the Substrate on the Electrical Resistance of Polymer Films," J. Oil Col. Chem. Assoc., 58, 155 (1975).

99. Kinsella, E. M. and Mayne, J. E. O., "Ionic Conduction in Polymer Films. I. Influence of Electrolyte on Resistance," Br. Polym. J., 1, 173 (1969).

100. Rajagopalan, K. S., Guruviah, S. and Rajagopalan, C. S., "Evaluation of Varnishes by Capacitance and Resistance Measurements," J. Oil Col. Chem. Assoc., 63, 144 (1980).

101. Brasher, D. M. and Nurse, T. J., "Electrical Measurements of Immersed Paint Coatings on Metal. II. Effect of Osmotic Pressure and Ionic Concentration of Solution on Paint Breakdown," J. Appl. Chem., 9, 96 (1959).

102. Kendig, M. W., and Leidheiser, Jr., H., "The Electrical Properties of Protective Polymer Coatings as Related to Corrosion of the Substrate," J. Electrochem. Soc.: Electrochemical Science and Technology, 123, No. 7, 982, (1976).

103. Maitland, C. C., and Mayne, J. E. O., "Factors Affecting the Electrolytic Resistance of Polymer Films," Official Digest, 34, 972 (1962).

104. Mills, D. J., and Mayne, J. E. O., "The Inhomogeneous Nature of Polymer Films and Its Affect on Resistance Inhibition," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August, 1980.

105. Brown, J. R., "Evaluation of Protective Coatings for Ship Bottoms," Corrosion, 15, No. 6, 49 (1959).

106. Hearst, P. J., "Electrical Properties of Coatings as Related to Performance. II. Experiments with Seven Additional Immersed Coatings Systems," U. S. Naval Civil Engineering Laboratory, Port Hueneme, CA, Tech. Note N-885, 1967.

107. Piens, M. and Verbist, R., "Electrochemical Values - Their Significance When Applied to a Coated Substrate," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August 1980.

108. Scantlebury, J. D. and Sussex, G. A. M., "Impedance Techniques for the Study of Organic Coatings," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August 1980.

109. Standish, J. and Leidheiser, Jr., H., "Properties and Behavior of Corrosion-Protective Organic Coatings Determined by Electrical Impedance Measurements," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August 1980.

110. Dévay, J., Mészáros, L., and Janászik, F., "Electro-Chemical Techniques to Monitor Performance of Polymer Coatings in Corrosion Protection," Ind. Eng. Prod. Res. Dev. 28, 13 (1979).

111. Gentles, J. K., "The Use of the Capacitance Cell in the Prediction of Paint Performance," J. Oil Col. Chem. Assoc., 46, 850 (1963).

112. O'Brien, H. C. "Some Laboratory Evaluations of Bituminous Coatings," Ind. Eng. Chem., 58, No. 6, 45 (1966).

113. Yassen, M. and Funke, W., "Effect of Temperature on Water Adsorption and Permeation Properties of Coatings," J. Oil Col. Chem. Assoc., 62, 284 (1979).

114. Guruviah, S., "The Relationship Between the Permeation of Oxygen and Water Through Paint Films and Corrosion of Painted Mild Steel," J. Oil Col. Chem. Assoc., 53, 669, (1970).

115. Funke, W. and Haagen, H., "Empirical or Scientific Approach to Evaluate the Corrosion Protective Performance of Organic Coatings," Ind. Eng. Chem. Prod. Res. Div., 17, No. 1, 80 (1978).

116. Murray, J. D., "Permeability Properties of Surface Coatings Toward Chloride Ion," J. Oil Col. Chem. Assoc., 56, 210 (1973).

117. Glass, A. L. and Smith, J., "A Radio Chemical Investigation Into the Diffusion of Ions Through Protective Films," Paint Technology, 38, No. 495, 203 (1966).

118. Glass, A. L. and Smith, J., "A Radiochemical Investigation on the Effect of Pigment on Diffusion of Ions Through Protective Films," J. of Paint Technology, 39, No. 511, 491 (1967).

119. Suoboda, M., Knapek, b. and Klicover, H., "The Effect of Pigments on the Penetration of Sulphur Dioxide into Coatings," J. Oil Col. Chem. Assoc., 56, 172 (1973).

120. Malik, W. U. and Aggarwal, L., "Ion Exchange Behavior of Some Anti-Corrosive Paints and Paint Media," J. Oil Col. Chem. Assoc., 57, 131 (1974).

121. Ruggeri, R. T. and Beck, T. R., "The Transport Properties of Polyurethane Paint," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August, 1980, p. 196.

122. Ulfuarson, U. and Khullar, M., "The Relationship Between the Ion Exchange Capacity and the Corrosion Protection Efficiency of Alkyd Based Anti-Corrosive Paints," J. Oil Col. Chem. Assoc., 54, 604 (1971).

123. Wang, W. and Leidheiser, Jr., "Delamination of Epoxy-Amino Coatings During Cathodic Treatment," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August 1980.

124. Corcoran, E. M., "Determining Stresses in Organic Coatings Using Plate Beam Deflection," J. Paint Technology, 41, No. 538, 635 (1969).

125. Farrar, N. R. and Ashbee, D. H. G., "Destruction of Epoxy Resins and of Glass-Fiber-Reinforced Epoxy Resins by Diffused Water," J. Phys. D: Appl. Phys., II, 1009 (1978).

126. Artamonova, R. V., Vinogradova, L. M., Garanina, S. D., Zherdev, Y. U. V., Korolev. A. Ya., "Internal Stresses and Water Diffusion in Polymers." Vysokomol. so ed. A12: No. 2, 336 (1970) (Translated in Polymer Sci. U.S.S.R. 12, No. 2, 385 (1970)).

127. Saarnak, A., Nilsson, E., and Kornum, L. O., "Usefulness of the Measurements of Internal Stresses in Paint Film," J. Oil Col. Chem. Assoc., 59, 427 (1976).

128. Croll, S. G., "Internal Stress in a Solvent-Cast Thermoplastic Coating," J. Coatings Technology, 50, No. 638, 33 (1978).

129. Croll, S. G., "Adhesion Loss Due to Internal Strain," J. Coatings Technology, 52, No. 665, 35 (1980).

130. Hill, L. W., "Stress Analysis - A Tool for Understanding Coatings Performance," Prog. in Org. Coatings, 5, 277 (1977).

131. Whiteley, P., Rothwell, G. W. and Kennedy, J., "Determination of Paint Films by Water," J. Oil Col. Chem. Assoc., 58, 200 (1975).

132. Talen, H. W., "The Mechanical Properties of Paint and Varnish Films," Paint and Varnish Production, 23, February 1961.

133. Kruger, J., "Use of Ellipsometry in the Study of Corrosion," Corrosion, 22, 88 (1966).

134. Ritter, J. J. and Kruger, J., "Studies on the Sub-Coating Environment of Coated Iron Using Qualitative Ellipsometric and Electrochemical Techniques," Corrosion Control by Organic Coatings Conference, Lehigh, PA, August 1980.

135. Gettings, M., Baker, F. S. and Kinlosch, A. J., Use of Auger and X-Ray Photo-Electron Spectroscopy to Study the Locus of Failure in Structural Adhesive Joints," J. Applied Polymer Sci., 21, 2375 (1977).

136. Hammond, J. S., Holubka, J. W. and Dickie, R. A., "On the Locus of Paint Adhesion in Failure in Corrosion," A. C. S. Org. Coat. Plas. Chem. 39, 506 (1978).

137. Hearst, P. J., "Effect of Atmospheric and Laboratory Irradiation on Attenuated Total Reflectance Spectra of Organic Coatings," Naval Civil Engineering Laboratory, Technical Note N-1411, 1975.

Appendix A. Reliability-Based Accelerated Aging Tests

The objective of accelerated aging tests is to make service life predictions at normal operating conditions from tests in which one or more of the stresses typically encountered in-service are operated at levels higher than normal. In operating at these high stress levels, it is presumed that the degradation process is accelerated but that the predominant failure mechanism is the same as that occurring in-service. Methods are available to verify these presumptions.

Mathematically, the accelerated aging process is stated as follows. Let Σ denote a vector of stresses to which the material is expected to be subjected in-service. Let S be any one of these stresses such that

$$S_0 < S_1 < \cdots < S_i < S_{i+1} < \cdots < \cdots < S_m. \tag{1}$$

That is, the ith level of this stress is less severe than the $(i + 1)$th level of stress; S_0 symbolizes the level of stress at normal conditions, and S_m symbolizes the most severe level of applied stress yet still obeying the imposed assumptions.

If now n specimens are randomly selected from a nominal population and subjected to stress level S_i, then each specimen will fail at some time T. Assuming all n specimens are exposed simultaneously, then the observed times to failure are ordered; that is

$$t_1 < t_2 < \cdots < t_2 < \cdots < t_r \text{ where } r < n.$$

These ordered times to failure form an empirical cumulative distribution function. To this empirical cumulative distribution function a theoretical cumulative distribution is fit such that the probability that a specimen will fail at or before time t is denoted by

$$F_{S_i}(t; \theta_i) = P_{S_i}(T < t) \tag{2}$$

where

$F_{S_i}(t)$ is the cumulative distribution function of the random variable T

for specimens subjected to stress S_i;

$P(\cdot)$ is the probability of the event in parentheses;

θ_i is a parameter vector for $F_{S_i}(t)$; and t is a time.

Assuming that the form of $F_{S_i}(t)$ does not change from stress level to stress level (the parameter vector θ is allowed to change) and assuming knowledge of $F_{S_i}(t)$ is available at two different stress levels, e.g., the ith and the $(i + 1)$th stress levels, then an acceleration of the degradation process has occurred if for all $t > 0$

35

$$F_{S_i}(t; \theta_i) < F_{S_{i+1}}(t; \theta_{i+1}) \qquad (3)$$

where $i = 1, 2, \ldots; m-1$. Given Eq. 3, a function, $\rho(t; S, \theta)$, exists relating the cumulative distribution function at any elevated stress level I to that at normal conditions.

$$F_{S_i}(t; \theta) = F_{S_0}(\rho(t; S, \theta)) \qquad (4)$$

where $\rho(t; S, \theta)$ is the acceleration function relating the parameter vector θ to applied stress S. Commonly, the acceleration function is assumed to be independent of exposure time; that is,

$$\rho(t; S, \theta) = \Psi(S, \theta) \cdot t \qquad (5)$$

Examples of $\Psi(S, \theta)$ include the Arrhenius model, the Eyring model, the inverse power law; and the William, Landell, and Ferry type superpositions. Assuming the inverse function $F_{S_0}^{-1}(t; \theta)$ exists, then $\rho(t; S, \theta_I))$ can be determined by

$$\rho(t; S, \theta) = F_{S_0}^{-1}(F_{S_I}(t; \theta_I)). \qquad (6)$$

It is the mission of accelerated aging programs to determine the acceleration function $\rho(t; S, \theta)$. Knowledge of this function, along with any cumulative distribution function at an elevated stress level $F_{S_I}(t; \theta_I)$ permits estimates of the cumulative distribution function at the normal stress level, $F_{S_0}(t; \theta)$, (see eq. 4).

The obvious advantages of this procedure are that once $\rho(t; S, \theta)$ is known, then drastic reductions in the accelerated aging program can be made by conducting accelerated aging tests at the maximum allowable stress S_m obeying the assumptions. Large savings in time are also realized since estimates of $F_{S_0}(t; \theta)$ can be made without observing all of the failure times. Perhaps the most important advantage of using this procedure is that coatings having like performance under similar conditions can now be grouped into performance classes, hence, any improvement on one coating system from the class may apply to all coatings in the class, thus effecting great savings in research.

NBS-114A (REV. 2-8C)

U.S. DEPT. OF COMM. **BIBLIOGRAPHIC DATA** **SHEET** *(See instructions)*	1. PUBLICATION OR REPORT NO. NBS TN 1149	2. Performing Organ. Report No.	3. Publication Date September 1981

4. TITLE AND SUBTITLE

Short-Term Evaluation Procedures for Coatings on Structural Steel

5. AUTHOR(S)

Paul G. Campbell, Jonathan W. Martin, and Mary E. McKnight

6. PERFORMING ORGANIZATION *(If joint or other than NBS, see instructions)* **NATIONAL BUREAU OF STANDARDS** **DEPARTMENT OF COMMERCE** **WASHINGTON, D.C. 20234**	7. Contract/Grant No. 8. Type of Report & Period Covered Final

9. SPONSORING ORGANIZATION NAME AND COMPLETE ADDRESS *(Street, City, State, ZIP)*

U.S. Department of Transportation
Federal Highway Administration
Washington, DC 20590

10. SUPPLEMENTARY NOTES

☐ Document describes a computer program; SF-185, FIPS Software Summary, is attached.

11. ABSTRACT *(A 200-word or less factual summary of most significant information. If document includes a significant bibliography or literature survey, mention it here)*

This report presents the findings of the first of a two-phased study to aid the Federal Highway Administration in evaluating and selecting protective coatings for steel. The objectives of the study are to review existing short-term test procedures for selecting coatings, and to discuss analytical measurement techniques for characterizing coating systems and for monitoring coating degradation.

In assessing current accelerated aging testing procedures, several deficiencies became apparent. These included the reported lack of reproducibility in the rankings for different iterations of the same short-term test and the lack of correlatability between the rankings of short-term laboratory and long-term outdoor exposure tests.

It was concluded that, at the present time, coating manufacturers and users do not depend heavily on accelerated test results for making durability assessments. Instead, durability assessments are based on outdoor exposure performance. Recommendations are made to design future short-term test procedures using reliability theory.

12. KEY WORDS *(Six to twelve entries; alphabetical order; capitalize only proper names; and separate key words by semicolons)*

accelerated aging tests; coatings; corrosion; time to failure; predictability; reproducibility.

13. AVAILABILITY ☒ Unlimited ☐ For Official Distribution. Do Not Release to NTIS ☒ Order From Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402. ☐ Order From Sup. of Doc., U.S. Government Printing Office, Washington, DC 20402.	14. NO. OF PRINTED PAGES 43 15. Price $3.00

USCOMM-DC 6043-P80

NBS TECHNICAL PUBLICATIONS

PERIODICALS

JOURNAL OF RESEARCH—The Journal of Research of the National Bureau of Standards reports NBS research and development in those disciplines of the physical and engineering sciences in which the Bureau is active. These include physics, chemistry, engineering, mathematics, and computer sciences. Papers cover a broad range of subjects, with major emphasis on measurement methodology and the basic technology underlying standardization. Also included from time to time are survey articles on topics closely related to the Bureau's technical and scientific programs. As a special service to subscribers each issue contains complete citations to all recent Bureau publications in both NBS and non-NBS media. Issued six times a year. Annual subscription: domestic $13; foreign $16.25. Single copy, $3 domestic; $3.75 foreign.

NOTE: The Journal was formerly published in two sections: Section A "Physics and Chemistry" and Section B "Mathematical Sciences."

DIMENSIONS/NBS—This monthly magazine is published to inform scientists, engineers, business and industry leaders, teachers, students, and consumers of the latest advances in science and technology, with primary emphasis on work at NBS. The magazine highlights and reviews such issues as energy research, fire protection, building technology, metric conversion, pollution abatement, health and safety, and consumer product performance. In addition, it reports the results of Bureau programs in measurement standards and techniques, properties of matter and materials, engineering standards and services, instrumentation, and automatic data processing. Annual subscription: domestic $11; foreign $13.75.

NONPERIODICALS

Monographs—Major contributions to the technical literature on various subjects related to the Bureau's scientific and technical activities.

Handbooks—Recommended codes of engineering and industrial practice (including safety codes) developed in cooperation with interested industries, professional organizations, and regulatory bodies.

Special Publications—Include proceedings of conferences sponsored by NBS, NBS annual reports, and other special publications appropriate to this grouping such as wall charts, pocket cards, and bibliographies.

Applied Mathematics Series—Mathematical tables, manuals, and studies of special interest to physicists, engineers, chemists, biologists, mathematicians, computer programmers, and others engaged in scientific and technical work.

National Standard Reference Data Series—Provides quantitative data on the physical and chemical properties of materials, compiled from the world's literature and critically evaluated. Developed under a worldwide program coordinated by NBS under the authority of the National Standard Data Act (Public Law 90-396).

NOTE: The principal publication outlet for the foregoing data is the Journal of Physical and Chemical Reference Data (JPCRD) published quarterly for NBS by the American Chemical Society (ACS) and the American Institute of Physics (AIP). Subscriptions, reprints, and supplements available from ACS, 1155 Sixteenth St., NW, Washington, DC 20056.

Building Science Series—Disseminates technical information developed at the Bureau on building materials, components, systems, and whole structures. The series presents research results, test methods, and performance criteria related to the structural and environmental functions and the durability and safety characteristics of building elements and systems.

Technical Notes—Studies or reports which are complete in themselves but restrictive in their treatment of a subject. Analogous to monographs but not so comprehensive in scope or definitive in treatment of the subject area. Often serve as a vehicle for final reports of work performed at NBS under the sponsorship of other government agencies.

Voluntary Product Standards—Developed under procedures published by the Department of Commerce in Part 10, Title 15, of the Code of Federal Regulations. The standards establish nationally recognized requirements for products, and provide all concerned interests with a basis for common understanding of the characteristics of the products. NBS administers this program as a supplement to the activities of the private sector standardizing organizations.

Consumer Information Series—Practical information, based on NBS research and experience, covering areas of interest to the consumer. Easily understandable language and illustrations provide useful background knowledge for shopping in today's technological marketplace.

*Order the **above** NBS publications from: Superintendent of Documents, Government Printing Office, Washington, DC 20402.*

*Order the **following** NBS publications—FIPS and NBSIR's—from the National Technical Information Services, Springfield, VA 22161.*

Federal Information Processing Standards Publications (FIPS PUB)—Publications in this series collectively constitute the Federal Information Processing Standards Register. The Register serves as the official source of information in the Federal Government regarding standards issued by NBS pursuant to the Federal Property and Administrative Services Act of 1949 as amended, Public Law 89-306 (79 Stat. 1127), and as implemented by Executive Order 11717 (38 FR 12315, dated May 11, 1973) and Part 6 of Title 15 CFR (Code of Federal Regulations).

NBS Interagency Reports (NBSIR)—A special series of interim or final reports on work performed by NBS for outside sponsors (both government and non-government). In general, initial distribution is handled by the sponsor; public distribution is by the National Technical Information Services, Springfield, VA 22161, in paper copy or microfiche form.

U.S. DEPARTMENT OF COMMERCE
National Bureau of Standards
Washington, DC 20234

———

OFFICIAL BUSINESS

Penalty for Private Use, $300